

Data sheet

Superwool® 351-E Paper

ENGLISH

Metric/Imperial information - Page 2

Description

Superwool papers are uniquely designed from Superwool bulk and organic binders. Superwool papers are specially processed to offer excellent performance in high-temperature applications. Superwool papers offer an alternative to traditional solutions due to its unique properties of high refractoriness and excellent non-wetting characteristics to applications requiring direct contact with molten aluminium.

Superwool 351-E expandable paper is an intumescent material produced and at maximum expansion which occurs at approximately 649°C (1200°F), the paper expands up to 400% of its thickness. This results in the 351-E paper being an excellent candidate for high temperature gaskets and seals, and fire protection applications. During heat up and expansion, there will be some additional out-gassing of the intumescent additives.

Chemical Properties

A small amount of organic combustible binder will burn out at approximately 149°C (300°F). Caution should be exercised during the initial heating. Adequate ventilation should be provided to avoid potential flash ignition of the binder out-gassing or avoid air entry while at elevated temperature.

Type

Paper manufactured from high temperature insulation wool.

Classification temperature

1100°C (2012°F)

The maximum continuous use temperature depends on the application. Unaffected by most chemicals except strong alkalis, phosphoric acid and molybdenum. For further advise please contact your local Morgan Advanced Materials representative.

Typical applications

- Industrial and domestic appliance gasketing
- Fire protection
- Fire doors
- Expansion joint insulation
- Fireplace catalytic converter gasketing
- Aluminum filter bowl gasketing

Benefits

- Low biopersistence
- Excellent thermal insulating performance
- Thin, flexible high temperature insulation
- Expansion up to 400%
- Low heat storage
- Excellent tensile strength
- Low thermal conductivity
- Non-wetting to molten aluminium
- Superwool fibres are exonerated and are not classified as carcinogenic by IARC or under any national regulations on a global basis. They have no requirements for warning labels under GHS (Globally Harmonised System for the classification and labelling of chemicals). In Europe, Superwool fibres meet the requirements specified under NOTA Q of European Directive 67/548. All Superwool fibre products are therefore exempt from the classification and labelling regulation in Europe.



Data sheet

Superwool® 351-E Papers

Paper Product Name	Superwool 351-E Paper
Fiber Class	AES
Physical Properties	
Manufacturing location	NA
Color	gray
Continuous Use Temperature, °C (°F)	1000 (1832)
Classification Temperature, °C (°F)	1100 (2012)
Melting Temperature, °C (°F)	1275 (2327)
Density, kg/m ³ (pcf)	240 - 288 (16 - 19)
Tensile strength, MPa (psi)	0.52 - 0.69 (75 - 100)
Fired Tensile strength, Mpa (psi)	0.03 - 0.07 (5 - 10)
Expansion Characteristics, % increase	
Thickness, in (mm)	3.17 (1/8)
400°F (204°C)	86
1004°F (540°C)	419
1454°F (790°C)	414
1798°F (981°C)	358
Chemical Analysis, % weight basis after firing	
Alumina, Al ₂ O ₃	trace
Silica, SiO ₂	55-65
Calcium oxide + Magnesium oxide, CaO + MgO	23-37
Carbon, C	5-10
Organic binder	6-10
Other	trace

Availability and Packaging

North America packaging

Thickness, mm (in)	Width, mm (in)	Sq M/Roll (Sq Ft/Roll)	Mill Rolls, Linear M/Roll (Ft/Roll)
2 (1/16)	610 (24)	46 (500)	229 (750)
	1220 (48)		
3 (1/8)	610 (24)	23 (250)	114 (375)
	1220 (48)		
6 (1/4)	610 (24)	12 (125)	56 (185)
	1220 (48)		

Contact

Europe:

Telephone:

+44 (0) 151 334 4030

E-mail:

marketing.tc@morganplc.com

North America:

Telephone:

+1 (706) 796 4200

E-mail:

northamerica.tc@morganplc.com

South America:

Telephone:

+54 (11) 4373 4439

E-mail:

marketing.tc@morganplc.com

Asia:

Telephone:

+65 6595 0000

E-mail:

asia.mc@morganplc.com

Whilst the values and application information in this datasheet are typical, they are given for guidance only. The values and the information given are subject to normal manufacturing variation and may be subject to change without notice. Morgan Advanced Materials – Thermal Ceramics makes no guarantees and gives no warranties about the suitability of a product and you should seek advice to confirm the product's suitability for use with Morgan Advanced Materials - Thermal Ceramics.

SUPERWOOL® is a patented technology for high temperature insulation wools which have been developed to have a low bio-persistence (information upon request). **SUPERWOOL®** products may be covered by one or more of the following patents, or their foreign equivalents:

SUPERWOOL® PLUS and **SUPERWOOL® HT** products are covered by patent numbers: US5714421 and US7470641, US7651965, US7875566, EP1544177 and EP1725503 respectively.

A list of foreign patent numbers is available upon request to Morgan Advanced Materials plc.

Morgan Advanced Materials plc Registered in England & Wales at Quadrant, 55-57 High Street, Windsor, Berkshire SL4 1LP UK Company No. 286773