

EST™ G Paper

Product Data Sheet



Product Description

EST G Paper is a composite product commonly used in lithium ion pack level protection.

EST G Paper is developed with Superwool® bulk fibres composition. The paper is encapsulated with a glass fibre cloth using specialty adhesive and sealing processes.

The glass fibre cloth provides good mechanical strength and protects the battery and people from fibers and dust. The product is also designed to protect the battery from external fire and heat.

Superwool fibres provide stability and resistance to chemical attack. Exceptions include hydrofluoric acid, phosphoric acid and strong alkalis (i.e. NaOH, KOH). Superwool is unaffected by incidental spills of oil or water. Thermal and physical properties are restored after drying.

Benefits

- Meets UL94 V-0 requirements
- High dielectric strength
- Excellent surface finish
- Lightweight
- Adhesive capable design

Applications

- Pack level protection of Lithium Ion batteries

Environmental & Health Safety

Superwool low biopersistent fibres manufactured by Morgan Advanced Materials are not classified as carcinogenic by IARC or under any national regulations on a global basis. They have no requirements for warning labels under GHS (Globally Harmonised System for the classification and labelling of chemicals).

In Europe, Superwool fibres meet the requirements specified under Note Q of European Regulation EC/1272/2008 (on Classification, Labelling and Packaging of substances and mixtures). All Morgan Advanced Materials Superwool low biopersistent fibre products are therefore exonerated from classification and labelling as hazardous in Europe.

EST™ G Paper

Product Data Sheet



| EST G Paper | |
|---|---------------------------|
| Colour | White / Off-White |
| Classification Temperature, °C (°F) | 1100 - 1300 (2010 - 2370) |
| Density, kg/m ³ (pcf) | 240 - 300 (15 - 19) |
| Tensile strength, kPa (psi) | >350 (>50) |
| Loss of ignition, % | ≤8 |
| Dielectric Breakdown, kΩ, kV/mm | >2 |
| Thickness, mm (in) | 1 - 6 (0.04 - 0.24) |
| UL94 Rating | UL94V-0 |
| Thermal Conductivity, W/m•K (BTU•in/hr•ft ² •°F), Descending | |
| 200°C (392°F) | 0.05 (0.35) |
| 400°C (752°F) | 0.07 (0.49) |
| 600°C (1112°F) | 0.11 (0.76) |
| 800°C (1472°F) | 0.16 (1.11) |
| 1000°C (1832°F) | 0.23 (1.60) |

The product(s) represented are intended for industrial refractory applications. The values and application information in this datasheet are given for guidance only. The values and the information given are subject to normal manufacturing variation and may be subject to change without notice. Morgan Advanced Materials – Thermal Ceramics makes no guarantees and gives no warranties about the suitability of a product, and you should seek advice to confirm the product's suitability for use with Morgan Advanced Materials.