

Kaowool® Blanket

Datasheet Code US: 5-14-205

Kaowool® Blanket is produced from kaolin clay by the blowing process and offers excellent handlability, high temperature stability and unparalleled dimensional tolerances SDS: 201



Features

- · Low thermal conductivity
- · Excellent thermal shock resistance
- Low heat storage capacity
- No organic binders

Applications

- Furnace Linings
- · Kiln Linings
- Boiler Insulation
- Furnace Door Seals
- Duct Lining
- Pipe Wrap Insulation
- · Investment Casting Mould Wrap
- Heat Shields
- · Field Stress Relieving
- Removable Thermal Insulation Pads
- Steam and Gas Turbine Insulation

The values given herein are typical average values obtained in accordance with accepted test methods and are subject to normal manufacturing variations. They are supplied as a technical service and are subject to change without notice. Therefore, the data contained herein should not be used for specification purposes. Check with your Morgan Advanced Materials office to obtain current information.



Kaowool® Blanket

Datasheet Code US: 5-14-205 SDS: 201

| Blanket Product Name | <u>Kaowool</u> |
|--|----------------|
| Fiber Class | RCF |
| Physical Properties | |
| Color | off-white |
| Continuous Use Temperature, °F | 2000 |
| Continuous Use Temperature, °C | 1093 |
| Classification Temperature, °F | 2300 |
| Classification Temperature, °C | 1260 |
| Density, pcf | 4, 6, 8 |
| Denisty, kg/m³ | 64, 96, 128 |
| Chemical Analysis, % weight basis after firing | |
| Alumina, Al ₂ O ₃ | 45 |
| Silica, SiO ₂ | 50-55 |
| Ferric oxide, Fe ₂ O ₃ | 1.0 |
| Titanium oxide, TiO ₂ | 2.2 |
| Alkalies, NaO ₂ + K ₂ O | 0.2 |
| Other | trace |
| Leachable Chlorides, ppm | 1-2 |
| Thermal Conductivity, BTU•in/hr•ft², per ASTM C201 | |
| Density, pcf | <u>8</u> |
| 500°F | 0.44 |
| 1000°F | 0.87 |
| 1500°F | 1.45 |
| 2000°F | 2.09 |
| Thermal Conductivity, W/m•K, per ASTM C201 | |
| Density, kg/m ³ | <u>128</u> |
| 260°C | 0.06 |
| 538°C | 0.12 |
| 816°C | 0.21 |
| 1093°C | 0.3 |

Availability and Packaging

Kaowool Blankets are packaged in cartons and stretch-wrapped onto pallets. Some size and density combinations may require a minimum order. Please check with your Thermal Ceramics office for current lead times and availability.

| Thickness, | Density, lb/ft³ (kg/m³) | | | | | ft ² (m ²)/carton for 24 |
|------------|-------------------------|--------|---------|-------------------|-----------------------|---|
| inch (mm) | 4 (64) | 6 (96) | 8 (128) | Length, inch (mm) | Width, inch (mm) | inch (610mm) width rolls |
| 1/4 (6) | | 0 | 0 | 240 (6095) | 24, 48 (610, 1220) | 160 (14.9) |
| 1/2 (13) | 0 | 0 | 0 | 600 (15240) | | 100 (9.3) |
| 1 (25) | 0 | | | 300 (7620) | | 50 (4.6) |

o = Kaowool

The values given herein are typical average values obtained in accordance with accepted test methods and are subject to normal manufacturing variations. They are supplied as a technical service and are subject to change without notice. Therefore, the data contained herein should not be used for specification purposes. Check with your Morgan Advanced Materials office to obtain current information.